

**CENTURY Grasse REGULUS B2**

|                     | Method     | Min | Max | Typical                         |
|---------------------|------------|-----|-----|---------------------------------|
| Color               |            |     |     | Amber                           |
| Texture             |            |     |     | Smooth                          |
| Thickening agent    |            |     |     | Lithium 12 hydroxi -<br>stearic |
| Dropping point (°C) | ASTM D 566 | 185 |     | 190                             |
| Penetration (mm/10) | ASTM D217  |     |     | 275                             |
| unworked            |            |     |     | 285                             |

|                          |            |     |      |      |
|--------------------------|------------|-----|------|------|
| Worked 60 x              |            | 265 | 295  | 280  |
| Worked 100.000 x (%)     |            |     | +10  | +7   |
| Acidity (%)              | ASTM D 128 |     | 0.3  | 0    |
| Alkalinity (%)           | ASTM D 128 |     | 0.2  | 0.06 |
| Water content (%)        | ISO 3733   |     | 0.1  | 0.05 |
| Water resistance         | DIN 51807  |     | 1-90 | 1-90 |
| Base oil specification   |            |     |      |      |
| Viscosity at 40°C (Cst)  | ASTM D 445 |     |      | 100  |
| Viscosity at 100°C (Cst) | ASTM D 445 |     |      | 10.0 |
| Flash point (°C)         | ASTM D 93  |     |      | 230  |